



# FlexiTank™

## AQUALINE™ 1850

<b>Base fabric</b>		Polyester
<b>Yarn</b>		6000/4000 Denier
<b>Construction</b>		10 x 5 cm
<b>Coating</b>		PVC/PU blend
<b>Total weight</b>		1850 g/m <sup>2</sup>
<b>Tensile strength</b>	DIN 53354	18275/5610 N/50mm
<b>Tear strength</b>	DIN 53363	2890/1530 N
<b>Adhesion Strength</b>	DIN 53357	205 N/5cm
<b>Elongation at break</b>		19% / 29%
<b>Surface Treatment</b>		1 side Matt Lacquered
<b>Temperature range</b>	DIN 53361	-30°C/70°C

Revision date: 06.12.2016/ Authorised by: GH

Data note: This data is based on average test results and supersedes any previous data. Dye stuffs used for various fibres and polymers have a tendency to migrate. We cannot guarantee that colour transfer will not occur if shades are mixed. Colour selection may change due to market requirements. Data shown is not legally binding.



Flexitank™ is a trademark of FloatPac Pty Ltd  
P: +61 (0) 3 9548 4700 | F: +61 (0) 3 9548 4744  
[info@floatpac.com](mailto:info@floatpac.com) | [www.floatpac.com](http://www.floatpac.com)  
PO Box 55, Mount Waverley, Victoria, 3149  
7/21-35 Ricketts Road, Mount Waverley, Victoria, 3149  
Aqualine 1850